



## JW-HT120N

N-type Single Glass Mono Black Module

370-390W



IEC61215(2016), IEC61730(2016) | ISO9001:2015: Quality Management System | ISO14001:2015: Environment Management System ISO45001:2018: Occupational health and safety management systems | IEC62941: 2019: Quality system for PV module manufacturing



#### **High Power Output**

MBB technology reduces the distance between busbars and finger grid lines, improving reliability and increasing output

$\frown$
( LID )
$\checkmark$

### ZERO LID (Light Induced Degradation)

N-type solar cell has no LID naturally which can increase power generation



#### **Higher Reliability**

Adpoted Jolywood lastest J-TOPCon2.0 technology, No polysilicon wrap around, Full electrical isolation, Zero leakage current; Much Safer for roof

#### Jolywood Delivers Reliable Performance Over Time

- Leader of N-type bifacial manufacturer
- Full-automatic facility and industry-leading technology
- Best-in-class durability and reliability
- BNEF Tier One



J-TOPCon 2.0 Technology

#### Better Weak Illumination Response

Higher power output even under low-light environments like on cloudy or foggy days

#### **Better Temperature Coefficient**


Higher power generation under working conditions, thanks to passivating contact cell technology



#### Lighter Module Weight

Reduces weight by more than 20% compared to bifacial double glass module

#### **Linear Performance Warranty**



\*Subject to the terms and conditions contained in the applicable Jolywood Solar Limited Warranty Statement. Also this 25 -year limited product warranty is available only for products installed and operating on residential rooftops in certain regions.



#### Testing Condition Front Side Front Side Front Side Front Side Front Side Peak Power (Pmax) (W) 370 375 380 385 390 MPP Voltage (Vmp) (V) 34.5 34.7 34.9 35.1 35.3 MPP Current (Imp) (A) 10.73 10.81 10.97 11.05 10.89 Open Circuit Voltage (Voc) (V) 41.4 41.6 41.8 42.0 42.2 Short Circuit Current (Isc) (A) 11.36 11.45 11.54 11.62 11.69 Module Efficiency (%) 20.28 20.55 20.83 21.10 21.38

\*STC: Irradiance 1000 W/m<sup>2</sup>, Cell Temperature 25°C, AM1.5 The data above is for reference only and the actual data is in accordance with the pratical testing Power Measurement Tolerance ±3%

#### Electrical Properties | NOCT\*

Testing Condition	Front Side				
Peak Power (Pmax) (W)	280	284	288	292	296
MPP Voltage (Vmp) (V)	32.4	32.6	32.8	33.0	33.2
MPP Current (Imp) (A)	8.65	8.72	8.78	8.84	8.91
Open Circuit Voltage(Voc)(V)	39.6	39.8	40.0	40.1	40.3
Short Circuit Current (Isc) (A)	9.16	9.23	9.30	9.37	9.43

\*NOCT: Irradiance 800 W/m<sup>2</sup>, Ambient Temperature 20°C, Wind Speed 1 m/s

# Operating Properties Operating Temperature (°C) -40°C~+85°C Maximum System Voltage (V) 1500V DC (IEC) Maximum Series Fuse Rating (A) 25 Power Tolerance 0~+5W

Temperature Coefficient	
Temperature Coefficient of Pmax*	-0.300%/°C
Temperature Coefficient of Voc	-0.250%/°C
Temperature Coefficient of Isc	+0.045%/°C
Nominal Operating Cell Temperature (NOCT)	42±2℃

\*Temperature Coefficient of Pmax±0.03%/°C


#### Mechanical Propertie

Cell Size	166.00mm*83.00mm
Number of Cells	120pcs(12*10)
Module Dimension	1756mm*1039mm*30mm
Weight	20kg
Front Glass*	3.2mm
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm²,+300mm/-180mm(Cable length can be customized )
*Heat strengthened glass	


#### Partner Sectior

NOTE :

#### Engineering Drawing (unit: mm



#### Characteristic Curves | HT120N-380



Packaging Configuration					
Packing Type	20'GP	40'GP	40'HQ		
Piece/Pallet		36			
Pallet/Container	6	13	26		
Piece/Container	216	468	936		

\*The specification and key features described in this datasheet may deviate slightly and are not guaranteed. Due to ongoing innovation, R&D enhancement,Jolywood (Taizhou) Solar Technology Co., Ltd. reserves the right to make any adjustment to the information described herein at any time without notice. Please always obtain the most recent version of the datasheet which shall be duly incorporated into the binding contract made by the parties governing all transactions related to the purchase and sale of the porducts described herein the related to the purchase.

SE

JOLYWOOD

JOLYWOOD (TAIZHOU) SOLAR TECHNOLOGY CO.,LTD. www.jolywood.cn Add: No.6 Kaiyang Rd., Jiangyan Economic Development Zone,Taizhou, Jiangsu Province, China, 225500 TEL: +86 523 80612799 Email: mkt@jolywood.cn

