





IEC61215(2016), IEC61730(2016) | ISO9001:2015: Quality Management System | ISO14001:2015: Environment Management System ISO45001:2018: Occupational health and safety management systems | IEC62941: 2019: Quality system for PV module manufacturing



10-30% Additional Power Generation

30 years lifespan brings 10-30% additional power generation comparing with conventional P-type module



ZERO LID (Light Induced Degradation)

N-type solar cell has no LID naturally which can increase power generation



Higher Reliability

Adpoted Jolywood lastest J-TOPCon2.0 technology, No polysilicon wrap around, Full electrical isolation, Zero leakage current; Much Safer for roof



- Leader of N-type bifacial manufacturer
- Full-automatic facility and industry-leading technology
- · Best-in-class durability and reliability
- BNEF Tier One



J-TOPCon 2.0

Better Weak Illumination Response

JOLYWOOD

Higher power output even under low-light environments like on cloudy or foggy days



Better Temperature Coefficient


Higher power generation under working conditions, thanks to passivating contact cell technology



Wider Applicability

More application scenes like BIPV, vertical installation, snowfield, high-humid, windy and dusty area

Linear Performance Warranty











Electrical Properties STC*					
Testing Condition	Front Side				
Peak Power (Pmax) (W)	375	380	385	390	395
MPP Voltage (Vmp) (V)	34.7	34.9	35.1	35.3	35.5
MPP Current (Imp) (A)	10.81	10.89	10.97	11.05	11.13
Open Circuit Voltage (Voc) (V)	41.6	41.8	42.0	42.2	42.4
Short Circuit Current (Isc) (A)	11.45	11.54	11.62	11.69	11.77
Module Efficiency (%)	20.55	20.83	21.10	21.38	21.65

*STC: Irradiance 1000 W/m², Cell Temperature 25°C, AM1.5
The data above is for reference only and the actual data is in accordance with the pratical testing Power Measurement Tolerance ±3%

Electrical Properties NOCT*					
Testing Condition	Front Side				
Peak Power (Pmax) (W)	284	288	292	296	299
MPP Voltage (Vmp) (V)	32.6	32.8	33.0	33.2	33.4
MPP Current (Imp) (A)	8.72	8.78	8.84	8.91	8.97
Open Circuit Voltage (Voc) (V)	39.8	40.0	40.1	40.3	40.5
Short Circuit Current (Isc) (A)	9.23	9.30	9.37	9.43	9.49

*NOCT: Irradiance 800 W/m², Ambient Temperature 20°C, Wind Speed 1 m/s

Operating Properties Operating Temperature (°C) -40°C~+85°C Maximum System Voltage (V) 1500V DC (IEC) Maximum Series Fuse Rating (A) 25 Power Tolerance 0~+5W Bifaciality* 80% *Bifaciality=Pmaxrear (STC) /Pmaxfront (STC) , Bifaciality tolerance:±5%

Temperature Coefficient	
Temperature Coefficient of Pmax*	-0.300%/°C
Temperature Coefficient of Voc	-0.250%/°C
Temperature Coefficient of Isc	+0.045%/°C
Nominal Operating Cell Temperature (NOCT)	42±2℃

^{*}Temperature Coefficient of Pmax±0.03%/°C

Mechanical Properties	
Cell Size	166.00mm*83.00mm
Number of Cells	120pcs(12*10)
Module Dimension	1756mm*1039mm*30mm
Weight	23kg
Front / Rear Glass*	2.0mm/2.0mm
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm², +300mm/-180mm (Cable length can be customized)

^{*}Heat strengthened glass


With Differ	With Different Power Generation Gain (regarding 380W as an example)					
Power Gain (%)	Peak Power (Pmax) (W)	MPP Voltage (Vmp) (V)	MPP Current (Imp) (A)	Open Circuit Voltage (Voc) (V)	Short Circuit Current (Isc) (A)	
10	410	34.9	11.75	41.8	12.44	
15	426	34.9	12.18	41.8	12.89	
20	441	35.0	12.61	41.9	13.34	
25	456	35.0	13.04	41.9	13.79	
30	471	35.0	13.47	41.9	14.24	

JOLYWOOD (TAIZHOU) SOLAR


TECHNOLOGY CO.,LTD.

www.jolywood.cn

Engineering Drawing (unit: mm



Characteristic Curves | HD120N-380



Packaging Configuration				
Packing Type	20'GP	40'GP	40'HQ	
Piece/Pallet		36		
Pallet/Container	6	13	26	
Piece/Container	216	468	936	

"The specification and key features described in this datasheet may deviate slightly and are not our quaranteed. Due to ongoing innovation, R&D enhancement, lolywood (Taizhbu) Solar Technology Co., Ltd. reserves the right to make any adjustment to the information described herein at any time without notice. Please always obtain the most recent version of the datashee transactions of the datashee and the please always obtain the most recent version of the datashee transactions related to the narrower and a large of the most of the plants of th



Add: No.6 Kaiyang Rd., Jiangyan Economic Development Zone,Taizhou, Jiangsu Province, China, 225500

TEL: +86 523 80612799 Email: mkt@jolywood.cn

